

Abstract

A magnetic recording medium containing a niobium-containing seedlayer having a thickness from about 1Å to about 40Å, and a method of making the same.

The seedlayer provides a recording media with relatively high remanent coercivity

5 and relatively high signal to medium noise ratio.

Patented by the U.S. Patent and Trademark Office